

TECHNICAL DATA SHEET

ITEM CODE 390PCR

HOT MELT ADHESIVE TAPE WITH 90% PCR POLYESTER BACKING

PRODUCT DESCRIPTION

Hot melt adhesive tape made with a solvent-free formulation based on synthetic rubbers and hydrocarbon resins. Characterized by a polyester film with 90% post-consumer recycled content (PCR) obtained from plastic bottles. Suitable for medium weight box sealing with manual dispensers or automatic carton sealing machines.



FEATURES



Noisy unwinding



Shipping fees optimization



Processing time optimization

MAIN APPLICATIONS









Medium weight box sealing



Automatic carton sealing machines



Space saving

90% PCR

backing

BACKING MATERIAL

90% POST-CONSUMER RECYCLED **BIORIENTATED POLYESTER**

TYPE OF ADHESIVE

HOT MELT

AVAILABLE VERSIONS

COLOURS

BROWN

WHITE



TRANSPARENT

TECHNICAL DATA	Metric	Values	Test method
Backing thickness	μm	19	AFERA 5006
Total thickness	μm	36	AFERA 5006
Adhesion to steel	N/cm	5	AFERA 5001
Tensile strength	N/cm	45	AFERA 5004
Elongation at break	%	100	AFERA 5004

Technical Informations, storage and product use

The product must be used within 12 months from the delivery date (6 months if jumbo). It is advisable to keep the material in its original packaging, away from heat sources and away from direct light. The storage temperature must be between 15° and 30° C and the relative humidity between 40 and 60%. For storage temperatures other than those indicated, recondition the product to the levels described above. The technical data shown in the data sheets are the average of the analyzes obtained on normal production. Aging can determine the variation of some technical and aesthetic characteristics of the product within the time limits indicated above without affecting its quality and functionality. The technical data shown are reported with a tolerance of +/- 10% and may be modified at any time for production needs or technical updates.

Fabo spa declines all responsibility for direct damage and for the consequences deriving from improper use of the product. It is advisable to check the conformity of the product in relation to the specific conditions of use.

Rev.00 10/06/2024



